



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET

ABLESTIK

ABLEBOND 8387

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Blue
Viscosity (cP): 9,500 @ 25°C
Tg Measured by DSC (°C): N/A
Tg Measured by TMA (°C): N/A
CTE Below Tg (ppm/°C): N/A
CTE Above Tg (ppm/°C): N/A

RECOMMENDED VFM CURE

VFM Cure Profile: 30 Seconds @ 120°C

Compared to Manufacturer's Suggested

Convection Oven Cure Profile: 5 Minutes @ 120°C

DSC COMPARISON

Ablebond 8387

