



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET EMERSON & CUMING AMICON C990

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Silver
Viscosity (cP): 21,000 – 60,000
Tg Measured by DSC (°C): N/A
Tg Measured by TMA (°C): N/A
CTE Below Tg (ppm/°C): N/A
CTE Above Tg (ppm/°C): N/A

RECOMMENDED VFM CURE

VFM Cure Profile: 18 Minutes @ 150°C

**Compared to Manufacturer's Suggested
Convection Oven Cure Profile: 60 Minutes @ 150°C**

DSC COMPARISON

Amicon C990

