



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET

EMERSON & CUMING

ECCOBOND 3193-17

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Gray
Viscosity (cP): N/A
Tg Measured by DSC (°C): N/A
Tg Measured by TMA (°C): N/A
CTE Below Tg (ppm/°C): N/A
CTE Above Tg (ppm/°C): N/A

RECOMMENDED VFM CURE

VFM Cure Profile: 12 Minutes @ 125°C

**Compared to Manufacturer's Suggested
Convection Oven Cure Profile: 20 Minutes @ 125°C**

DSC COMPARISON

Eccobond 3193-17

