



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET EMERSON & CUMING AMICON 1172

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Tan
Viscosity (cP): N/A
Tg Measured by DSC (°C): N/A
Tg Measured by TMA (°C): N/A
CTE Below Tg (ppm/°C): N/A
CTE Above Tg (ppm/°C): N/A

RECOMMENDED VFM CURE

VFM Cure Profile: 2 Minutes @ 150°C

Compared to Manufacturer's Suggested
Convection Oven Cure Profile: 4 Minutes @ 150 °C

DSC COMPARISON

Emerson & Cumming 1172

