



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET

EPO-TEK 375

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Straw / Red
Viscosity (cP): 2,000 – 4,000 @ 50 rpm / 25°C
Tg Measured by DSC (°C): N/A
Tg Measured by TMA (°C): 130
CTE Below Tg (ppm/°C): 48
CTE Above Tg (ppm/°C): 184

RECOMMENDED VFM CURE

VFM Cure Profile: 30 Seconds @ 150°C

Compared to Manufacturer's Suggested

Convection Oven Cure Profile: 5 Minutes @ 150°C

DSC COMPARISON

Epo-Tek 375

