



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET

LOCTITE

HYSOL & EA 9360

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Blue
Viscosity (cP): 1200
Tg Measured by DSC (°C): N/A
Tg Measured by TMA (°C): N/A
CTE Below Tg (ppm/°C): N/A
CTE Above Tg (ppm/°C): N/A

RECOMMENDED VFM CURE

VFM Cure Profile: 10 Minutes @ 82°C

Compared to Manufacturer's Suggested
Convection Oven Cure Profile: 60 Minutes @ 82°C

DSC COMPARISON

LOCTITE EA 9360

