



Microwave solutions for the next generation in advanced materials processing

## VFM TECHNICAL DATA SHEET

LOCTITE  
HYSOL 9492

### ADHESIVE PROPERTIES (As reported by manufacturer)

Color: White  
Viscosity (cP): N/A  
Tg Measured by DSC (°C): N/A  
Tg Measured by TMA (°C): N/A  
CTE Below Tg (ppm/°C): N/A  
CTE Above Tg (ppm/°C): N/A

### RECOMMENDED VFM CURE

VFM Cure Profile: 30 Sec @ 130°C

Compared to Manufacturer's Suggested  
Convection Oven Cure Profile: Room Temperature cure

### DSC COMPARISON

Loctite Hysol 9492

