



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET

LOCTITE

KO0125

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Silver
Viscosity (cP): 22,000
Tg Measured by DSC (°C):
Tg Measured by TMA (°C): 96
CTE Below Tg (ppm/°C): N/A
CTE Above Tg (ppm/°C): N/A

RECOMMENDED VFM CURE

VFM Cure Profile: 1 Minutes @ 165°C

Compared to Manufacturer's Suggested

Convection Oven Cure Profile: 10 Minutes @ 165°C

DSC COMPARISON

Loctite KO0125

