



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET

NAMICS

CHIPCOAT U8437-2

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Black
Viscosity (cP): N/A
Tg Measured by DSC (°C): N/A
Tg Measured by TMA (°C): 137
CTE Below Tg (ppm/°C): 32
CTE Above Tg (ppm/°C): 120

RECOMMENDED VFM CURE

VFM Cure Profile: 3 Minutes @ 150°C

Compared to Manufacturer's Suggested

Convection Oven Cure Profile: 20 Minutes @ 150°C

DSC COMPARISON

Namic U8437-2

