



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET

TRA-CON

TRA-DUCT 2919

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Silver
Viscosity (cP): 995,000
Tg Measured by DSC (°C): N/A
Tg Measured by TMA (°C): 170
CTE Below Tg (ppm/°C): N/A
CTE Above Tg (ppm/°C): N/A

RECOMMENDED VFM CURE

VFM Cure Profile: 2 Minutes @ 125°C

Compared to Manufacturer's Suggested
Convection Oven Cure Profile: 30 Minutes @ 125°C

DSC COMPARISON

TRA-DUCT 2919

