



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET

EMERSON & CUMING

UNISSET LA 3032-78

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Tan
Viscosity (cP): N/A
Tg Measured by DSC (°C): N/A
Tg Measured by TMA (°C): N/A
CTE Below Tg (ppm/°C): N/A
CTE Above Tg (ppm/°C): N/A

RECOMMENDED VFM CURE

VFM Cure Profile: 8 Minutes @ 100°C

**Compared to Manufacturer's Suggested
Convection Oven Cure Profile: 15 Minutes @ 100°C**

DSC COMPARISON

Uniset LA 3023-78

