



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET

ZYMET TC-201P

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: Cream / Tan
Viscosity (cP): 90,000
Tg Measured by DSC (°C): N/A
Tg Measured by TMA (°C): 90
CTE Below Tg (ppm/°C): 55
CTE Above Tg (ppm/°C): 180

RECOMMENDED VFM CURE

VFM Cure Profile: 3 Minutes @ 150°C

Compared to Manufacturer's Suggested

Convection Oven Cure Profile: 10 Minutes @ 150°C

DSC COMPARISON

Zymet TC-201P

