



Microwave solutions for the next generation in advanced materials processing

VFM TECHNICAL DATA SHEET

ZYMET X12422

ADHESIVE PROPERTIES (As reported by manufacturer)

Color: White
Viscosity (cP): N/A
Tg Measured by DSC (°C): 128
Tg Measured by TMA (°C): N/A
CTE Below Tg (ppm/°C): 33
CTE Above Tg (ppm/°C): N/A

RECOMMENDED VFM CURE

VFM Cure Profile: 1 Minutes @ 120°C

Compared to Manufacturer's Suggested

Convection Oven Cure Profile: 5 Minutes @ 120°C

DSC COMPARISON

Zymet X12422

